

SPECIFICATION CONTROL DRAWING

55A0712

TITLE WIRE, RADIATION-CROSSLINKED, MODIFIED, ETFE-INSULATED,
HEAVY DUTY, GENERAL PURPOSE, 1000 VOLT

Date 10-26-04


Revision B

This specification sheet forms a part of the latest issue of Raychem Specification 55A.

CONDUCTOR - SILVER-COATED COPPER

PRIMARY INSULATION -

RADIATION-CROSSLINKED
MODIFIED ETFE. Primary insulation
shall be of a contrasting pigmentation
to that of the jacket.



JACKET - RADIATION-CROSSLINKED,
MODIFIED ETFE

TABLE I. CONSTRUCTION DETAILS

PART NUMBER <u>1/</u>	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	DIAMETER OF STRANDED CONDUCTOR (in.)		MAXIMUM RESISTANCE AT 20°C (ohms/1000 ft)	FINISHED WIRE	
			MINIMUM	MAXIMUM		DIAMETER (in.)	MAXIMUM WEIGHT (lbs/1000 ft)
55A0712-24-*	24	19 x 36	.023	.025	24.3	.056 ± .003	3.3
55A0712-22-*	22	19 x 34	.029	.031	15.1	.062 ± .003	4.4
55A0712-20-*	20	19 x 32	.037	.039	9.19	.070 ± .003	6.1
55A0712-18-*	18	19 x 30	.046	.048	5.79	.080 ± .004	8.7
55A0712-16-*	16	19 x 29	.052	.054	4.52	.087 ± .004	10.7
55A0712-14-*	14	19 x 27	.065	.068	2.88	.103 ± .004	15.7
55A0712-12-*	12	37 x 28	.084	.087	1.90	.120 ± .006	22.9
55A0712-10-*	10	37 x 26	.106	.112	1.19	.144 ± .006	35.3
55A0712- 8-*	8	133 x 29	.158	.169	.658	.205 ± .008	64.6
55A0712- 6-*	6	133 x 27	.198	.213	.418	.251 ± .010	100.
55A0712- 4-*	4	133 x 25	.250	.268	.264	.320 ± .010	158.
55A0712- 2-*	2	665 x 30	.320	.340	.170	.418 ± .012	263.

TABLE II. PERFORMANCE DETAILS

PART NUMBER <u>1/</u>	BEND TESTING			
	MANDREL DIAMETER (inch) (± 3%)		WEIGHT (lb) (± 3%)	
	IMMERSION, LIFE CYCLE AND ACCELERATED AGING	COLD BEND	IMMERSION, LIFE CYCLE AND ACCELERATED AGING	COLD BEND
55A0712-24-*	1.00	1.25	2.00	4.00
55A0712-22-*	1.00	1.25	2.00	4.00
55A0712-20-*	1.00	1.25	3.00	5.00
55A0712-18-*	1.00	1.25	3.00	5.00
55A0712-16-*	1.25	1.50	3.50	5.50
55A0712-14-*	1.25	1.50	3.50	5.50
55A0712-12-*	2.00	3.00	4.00	6.00
55A0712-10-*	2.00	3.00	4.00	6.00
55A0712- 8-*	4.00	5.00	4.00	8.00
55A0712- 6-*	5.00	6.00	5.00	12.0
55A0712- 4-*	6.00	8.00	5.00	15.0
55A0712- 2-*	8.00	10.0	6.00	15.0

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.
Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL.

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN.
REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.

tyco
Electronics

Raychem Wire & Cable
501 Oakside Avenue
Redwood City, CA 94063-3800
Phone: 1-800-227-8816
Fax: 1-650-361-6297

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C

Maximum continuous conductor temperature

VOLTAGE RATING: 1000 volts (rms) at sea level

ACCELERATED AGING (CROSSLINKING PROOF): 300 ± 3°C for 7 hours

BLOCKING: 230 ± 3°C for 24 hours

COLOR: White preferred

CONCENTRICITY: 70% (minimum)

FLAMMABILITY: Procedure 1, 3 seconds (maximum); 3 in. (maximum); no flaming of facial tissue.

HUMIDITY RESISTANCE: Insulation Resistance,

5000 megohms for 1000 ft. (minimum) for AWG 24 -10,

3000 megohms for 1000 ft. (minimum) for AWG 8 - 2

IDENTIFICATION AND COLOR STRIPING DURABILITY:

125 cycles (250 strokes) (minimum), 500 g weight

INSULATION ELONGATION AND TENSILE STRENGTH:

Elongation, 50% (minimum)

Tensile strength, 5000 lbf/in² (minimum)

INSULATION FLAWS:

Primary Insulation,

Spark test, 1.5 kV (rms)

Impulse Dielectric Test, 6.0 kV (peak)

Finished Wire,

Spark test, 3.0 kV (rms)

Impulse Dielectric Test, 8.0 kV (peak)

INSULATION RESISTANCE:

5000 megohms for 1000 ft. (minimum) for AWG 24 -10,

3000 megohms for 1000 ft. (minimum) for AWG 8 - 2

INSULATION THICKNESS: 0.014 in. (minimum) for total insulation

LIFE CYCLE: 230 ± 3°C for 500 hours

LOW TEMPERATURE-COLD BEND: -65 ± 3°C for 4 hours

SHRINKAGE: 230 ± 3°C for 6 hours, 0.125 in. (maximum) in 12 in.

SMOKE TEST: 250 ± 5°C, No visible smoke

SURFACE RESISTANCE: 500 megohms-in. (minimum), both readings

THERMAL SHOCK RESISTANCE: 200 ± 3°C

0.060 in. (maximum) for AWG 24 - 12

0.100 in. (maximum) for AWG 10 - 8

0.125 in. (maximum) for AWG 6 - 2

VOLTAGE WITHSTAND TEST(Post Environmental): 2500 volts (rms), 60 Hz

PART NUMBER:

The "*" in the part numbers on page 1 shall be replaced by a color code designator.

1/ Example: AWG 22, white: 55A0712-22-9

AWG 22, white with black stripe: 55A0712-22-90

1/ See Footer section on page 1

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[TE Connectivity:](#)

[55A0712-22-96](#) [55A0712-22-90](#) [55A0712-22-9](#) [55A0712-22-92](#)

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9