



# DATA SHEET

Document number: TTDS-019  
Issue: 4  
Date: March 2014

## RPS Heat shrinkable sleeves

|                                     |                                                                                                                                                                                        |
|-------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>MATERIAL DESCRIPTION:</b>        | Thin wall, flame retarded radiation cross-linked polyolefin heat-shrinkable tubing, assembled as organized cut sleeves in a “ladder” configuration. 3:1 shrink ratio.                  |
| <b>USE:</b>                         | Identification of wires and cables by computer-based printing onto sleeves. Sleeves can also provide terminal insulation and strain relief. Suitable for many commercial applications. |
| <b>PRINT METHOD/RIBBON:</b>         | See document 411-121005 IDENTIFICATION PRINTER PRODUCT RIBBON MATRIX for the recommended printer/product/ribbon combination.                                                           |
| <b>SERVICE TEMPERATURE:</b>         | -30°C to +105°C (-22°F to +221°F).                                                                                                                                                     |
| <b>COLORS:</b>                      | White or yellow.                                                                                                                                                                       |
| <b>FLAMMABILITY:</b>                | Burn time <1 minute (UL 224, all tubing flame test).                                                                                                                                   |
| <b>LONGITUDINAL CHANGE:</b>         | 20% maximum on shrinking.                                                                                                                                                              |
| <b>TENSILE STRENGTH:</b>            | 8MPa minimum (ASTM D2671).                                                                                                                                                             |
| <b>ULTIMATE ELONGATION:</b>         | 150% minimum (ASTM D2671).                                                                                                                                                             |
| <b>MOLD GROWTH:</b>                 | 56 day incubation (ISO 846B) – tensile strength, ultimate elongation and Dielectric strength maintained after testing.                                                                 |
| <b>DIELECTRIC STRENGTH:</b>         | 19.7MV/m minimum.                                                                                                                                                                      |
| <b>MAXIMUM STORAGE TEMPERATURE:</b> | 40°C (104°F).                                                                                                                                                                          |
| <b>PRINT PERMANENCE:</b>            | Print legible after 20 rubs (SAE AS5942)<br>Print legible after 30 strokes (MIL-STD-202F, method 215J)                                                                                 |

While TE Connectivity Ltd. has made every reasonable effort to ensure the accuracy of the information in this document, TE does not guarantee that it is error-free, nor does TE make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. TE reserves the right to make any adjustments to the information contained herein at any time without notice. TE expressly disclaims all implied warranties regarding the information contained herein, including, but not limited to, any implied warranties of merchantability or fitness for a particular purpose. The dimensions in this document are for reference purposes only and are subject to change without notice. Specifications are subject to change without notice. Consult TE for the latest dimensions and design specifications.



# DATA SHEET

Document number: TTDS-019  
Issue: 4  
Date: March 2014

## RPS Heat shrinkable sleeves

| THREAT                                                  | TEST                                          | EFFECT        |
|---------------------------------------------------------|-----------------------------------------------|---------------|
| Isopropyl Alcohol                                       | 24 hours at 23°C (73°F), SAE AS5942 (20 rubs) | Print legible |
| Gasoline (unleaded)                                     | 24 hours at 23°C (73°F), SAE AS5942 (20 rubs) | Print legible |
| Diesel Fuel, DF2                                        | 24 hours at 23°C (73°F); SAE AS5942 (20 rubs) | Print legible |
| Auto Engine Oil, SF<br>10W-40 (SAE J 183, SAE J<br>300) | 24 hours at 23°C (73°F); SAE AS5942 (20 rubs) | Print legible |
| Motor Vehicle Brake Fluid,<br>SAE J 1703                | 24 hours at 23°C (73°F); SAE AS5942 (20 rubs) | Print legible |
| Ethylene Glycol                                         | 24 hours at 23°C (73°F); SAE AS5942 (20 rubs) | Print legible |

Notes: See TE specification RW2510 for full RPS performance & dimensional details.

Some types of neoprene insulation used in jackets contain additives that can migrate to the surface and discolor the polyolefin RPS sleeves. Any discoloration is dependent on the composition of the neoprene, combined with application conditions. Users should independently evaluate the suitability of RPS sleeves for applications involving neoprene-jacketed cables.

## Данный компонент на территории Российской Федерации

**Вы можете приобрести в компании MosChip.**

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

### Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: [info@moschip.ru](mailto:info@moschip.ru)

Skype отдела продаж:

moschip.ru

moschip.ru\_4

moschip.ru\_6

moschip.ru\_9