3M Adhesive Transfer Tape with Quick Bonding Adhesive 360 9626 • 9627

Technical Data			Nove	ember, 2009
Product Description		surfaces, including mai	uick Bonding Adhesive ny low surface energy pl	
Construction	Product Number	Adhesive Type/ Thickness	Liner Color, Type, Print	Liner Caliper
	3M™ Adhesive Transfer Tape 9626	0.002" (0.05 mm)	Natural, 60# Glassine	0.0032" (0.08 mm)
	3M™ Adhesive Transfer Tape 9627	0.005" (0.13 mm)	Natural, 60# Glassine	0.0032" (0.08 mm)

Note: The caliper listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.071 g/cc.

3M[™] Adhesive Transfer Tape with Quick Bonding Adhesive 360 9626 • 9627

Typical Physical Properties and	Note: The following technical information and data should be considered representativ or typical only and should not be used for specification purposes.				
Performance Characteristics	Product Number	0.05 mm (2.0 mil) 3M™ Adhesive Transfer Tape 9626	0.13 mm (5.0 mil) 3M™ Adhesive Transfer Tape 9627		
	Adhesion to Polypropylene ASTM D3330 – 180 degree 2 mil al foil	Oz/in (N/25 mm) Faceside / Backside	Oz/in (N/25 mm) Faceside / Backside		
	- 30 seconds RT	100 (28) / 100 (28)	160 (45) / 150 (42)		
	- 15 minutes RT	100 (28) / 100 (28)	165 (46) / 155 (43)		
	- 72 hours RT	130 (36) / 120 (34)	165 (46) / 165 (46)		
	Adhesion to other surfaces ASTM D3330 – 180 degree, 2 mil al foil, 72 hour RT	Oz/in (N/25 mm) Faceside / Backside	Oz/in (N/25 mm) Faceside / Backside		
	ABS	140 (39) / 130 (36)	165 (46) / 165 (46)		
	Stainless Steel	140 (39) / 140 (39)	160 (45) / 160 (45)		
	Polycarbonate	140 (39) / 140 (39)	165 (46) / 165 (46)		
	LDPE	60 (17) / 55 (15)	95 (26) / 90 (25)		
	HDPE	70 (20) / 65 (18)	80 (22) / 80 (22)		
	Shear Strength - ASTM D3654 Modified – (.5 inch² sample size)				
	1000 grams at 72°F (22°C)	>10,000 minutes	>10,000 minutes		
	500 grams at 158°F (70°F)	>10,000 minutes	>10,000 minutes		
	Relative High Temperature Operating Ranges:				
	Long Term (days, weeks)	200°F (93°C)	200°F (93°C)		
	Short Term (minutes, hours)	350°F (177°C)	350°F (177°C)		
	Relative Solvent Resistance:	Very Good	Very Good		

Available Sizes

Roll length, width, slitting tolerance, core size.

Product	3M [™] Adhesive Transfer Tape		
	9626	9627	
Maximum Length in.:			
1/2" to 1/2"	72 yds. (66 m)	72 yds. (66 m)	
1/2" to 1"	360 yds. (329 m)	252 yds. (230 m)	
1" to 6"	540 yds. (494 m)	540 yds. (494 m	
6" to 27"	900 yds. (823 m)	720 yds. (658 m)	
27" to 54"	540 yds. (494 m)	540 yds. (494 m)	
Normal Slitting Tolerance	± 1/32 in. (0.08 mm)		
Core Size (ID)	3.0 in. (76.2 mm)		
Minimum length	72 yds. (66 m).		

3M[™] Adhesive Transfer Tape with Quick Bonding Adhesive 360 9626 • 9627

Features	• Excellent adhesion to difficult to bond to surfaces such as HDPE, LDPE, and PP.		
	 Super quick stick. Higher adhesion from a thinner tana 		
	Higher adhesion from a thinner tape.Excellent solvent resistance.		
	High temperature performance.		
Application Techniques	Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application will assist the adhesive in developing intimate contact with the bonding surface. To accelerate the adhesion process, additional heat, up to 130°F (54°C), may be used.		
	To obtain optimum adhesion, the bonding surfaces must be clean, dry, and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.*		
	Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.		
	*When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturers precautions and directions for use. These cleaning recommendations may not be compliant with the rules of certain Air Quality Management Districts in California; consult applicable rules before use.		
Environmental Performance	Humidity Resistance: High humidity has minimal effect on adhesive performance. No significant reduction in bond strength is observed after exposure for 7 days at 90°F (32°C) and 90% relative humidity.		
	UV Resistance: When properly applied, nameplates and decorative trim parts are not adversely affected by exposure.		
	Water Resistance: Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.		
	Temperature Cycling Resistance: High bond strength is maintained after cycling four times through:		
	8 hours at 194°F (90°C) 16 hours at -40°F (-40°C) 8 hours at 100.4°F (38°C/100% RH) 16 hours at -40°F (-40°C)		
	Chemical Resistance: When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids, and alkalis.		
Application Ideas	Foam to powder coated painted surfaces.		
	• Low surface energy plastic adhesion.		
	- 3 -		

3MTM Adhesive Transfer Tape with Quick Bonding Adhesive 360 9626 • 9627

Application Equipment	To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, $3M^{\text{TM}}$ Lamination Techniques for Converters of Laminating Adhesives (70-0704-1430-8).
	For additional dispenser information, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.
Storage	Store in original cartons at 70°F (21°C) and 50% relative humidity.
Shelf Life	If stored under proper conditions, product retains its performance and properties for two years from date of manufacture.
Technical Information	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.
Product Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.
	(ISO 9001:2000)
	This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards

3M

Industrial Adhesives and Tapes Division Converter Markets

3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-223-7427 • 651-778-4244 (fax) www.3M.com/converter

Recycled Paper 40% pre-consumer 10% post-consumer

3M is a trademark of 3M Company. Printed in U.S.A. ©3M 2009 70-0713-4543-6 (11/09)





Общество с ограниченной ответственностью «МосЧип» ИНН 7719860671 / КПП 771901001 Адрес: 105318, г.Москва, ул.Щербаковская д.З, офис 1107

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

http://moschip.ru/get-element

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж: moschip.ru moschip.ru_4

moschip.ru_6 moschip.ru_9