

3M™ Electrical Tape 44

Data Sheet

January 2011

Description 3M™ Electrical Tape 44 is a low-halogen, combination polyester film/polyester web film coated with a rubber thermosetting pressure-sensitive adhesive. This UL recognized conformable tape is puncture resistant with excellent electrical properties.

Agency Approvals & Self Certifications Meets requirements of:
UL File No. E17385, Guide OANZ2
For temperatures not exceeding 130°C

Applications Used for stick-wound coils/transformers and in bobbin-wound coils for banding, anchoring, and insulating, and for protecting start wires, leads, terminal strips, insulation paper, end turns and connections in motors and transformers.

Typical Properties Not for specifications. Values are typical, not to be considered minimum or maximum. Properties measured at room temperature 73°F (23°C) unless otherwise stated.

Physical Properties (Test Method) (ASTM D1000 unless noted)	Typical Value US units (metric)
Color	Caramel Translucent
Adhesive	Rubber Thermosetting
Backing Thickness	5.5 mils (0,139 mm)
Breaking Strength	40 lbs/in (70 N/10 mm)
Elongation (% at break)	50%
Puncture Resistance (per Federal Spec L-T-001512)	12 lbs (5.4 kg)
Adhesion to Steel	65 oz/in (7.1 N/10 mm)
Halogen Content	Chlorine <0.09% Bromine <0.004%

Electrical Property (Test Method) (ASTM D1000 unless noted)	Typical Value US units (metric)
Dielectric Breakdown	5500 V
Insulation Resistance	>1 x 10 ⁶ megohms
CTI Material Group	I = (> 600 volts)
Electrolytic Corrosion Factor (3M TM)	1.0

3M™ Electrical Tape 44

Specifications

3M™ Electrical Tape 44 is a low-halogen, polyester web-reinforced film with thermosetting rubber, pressure-sensitive adhesive.

The tape shall be coated on one side with pressure-sensitive adhesive, which shall not require heat, moisture or other preparation prior to or subsequent to application. The adhesive coating shall be smooth and uniform and be free of lumps and bare spots. There shall be no separator between adjacent layers of the roll. The tape shall perform at a temperature of 262°F (130°C) without loss of physical or electrical properties

For maximum solvent resistance and holding properties, the tape should be thermoset at one of the following cycles:

1 hour @ 300° F (150° C)

2 hours @ 275° F (135° C)

3 hours @ 250° F (120° C)

Shelf Life & Storage

This product has a 5-year shelf life from date of manufacture when stored in a humidity controlled storage (10°C/50°F to 27°C/80°F and <75% relative humidity).

Availability

Please contact your local distributor; available from 3M.com/electrical [Where to Buy] or call 1.800.676.8381.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M's current publications, or any contrary statements contained on your purchase order, shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability

This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.

3M is a trademark of 3M Company.

Electrical Markets Division
6801 River Place Blvd.
Austin, TX 78726-9000
800.676.8381
FAX: 800.828.9329
www.3M.com/electrical

Please recycle
© 3M 2011 All rights reserved
78-8124-4753-6 D

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9