



Electroplating Tape

470 • 470L

Technical Data

February, 2011

Product Description

3M™ Electroplating Tape 470 is a conformable and abrasion-resistant vinyl tape with excellent resistance to most chemicals used in typical electroplating processes. 3M™ Electroplating Tape 470L is a lined version of 3M vinyl tape 470 that may be used for die-cutting or large area applications.

Product Construction

Backing	Adhesive	Liner	Color	Standard Roll Length
Pigmented vinyl	Rubber	Tape 470 - none Tape 470L - white paper	Tan	36 yds. (33 m)

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

ASTM Test Method		
Adhesion to Steel:	37 oz./in. width (40.4 N/100 mm)	D-3330
Tensile Strength at Break:	20 lbs./in. width (350 N/100 mm)	D-3759
Elongation at Break:	180%	D-3759
Backing Thickness:	6.3 mils (0.16 mm)	D-3652
Total Tape Thickness (without liner):	7.1 mils (0.18 mm)	D-3652
Liner Thickness:	6.1 mils (0.15 mm)	D-3652
Temperature Use Range:	Up to 250°F (121°C)	

Features

- Excellent resistance to most chemicals used in typical electroplating operations.
- Prolonged exposure to elevated temperatures (above 250°F/121°C) and hot caustics may cause weakening of the adhesive bond.
- Can be qualified to meet Federal Specification HH-T-0025 (GSA-FSS) Amendment 2.
- Resists most common solvents, care should be taken to avoid ketones, chlorinated hydrocarbons, and esters, found in lacquer thinners, degreasers, paint strippers, etc., which may cause the backing to swell or curl.
- Vinyl backing is conformable
- Backing accepts marker ink and is printable in using the thermal transfer process.

3M™ Electroplating Tape

470 • 470L

Application Ideas

- Masking during many electroplating operations, including both flat strip and overlapping masks.
- Wrapping, patching, coated racks and masking many irregular surfaces.
- Labeling.
- Sealing containers from water intrusion.

Storage

Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% R.H. in the original carton.

Shelf Life

To obtain best performance, use this product within 18 months from date of manufacture.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2008

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2008 standards.

3M

Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-3550 • 877-369-2923 (Fax)
www.3M.com/industrial



Recycled Paper
40% pre-consumer
10% post-consumer

3M is a trademark of 3M Company.
Printed in U.S.A.
©3M 2011 70070950160 (2/11)

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9