



UHMW Polyethylene Tape

5421 · 5423

Technical Data

July, 2016

Product Description	3M™ UHMW Polyethylene Tapes are film coated with a rubber adhesive which provides an excellent abrasion resistant surface. These tapes feature a unique combination of properties that make it ideal for many tough impact wear or sliding applications. 3M™ UHMW-PE Film Tape 5421 is a thinner version of 3M™ UHMW-PE Film Tape 5423.			
----------------------------	---	--	--	--

Product Construction	Backing	Adhesive	Color	Standard Roll Length
	UHMW-PE Film (ultra-high molecular weight polyethylene)	Rubber	Translucent	36 yds. (32.9 m)

Typical Physical Properties	Note: The following technical information and data should be considered representative or typical only, and should not be used for specification purposes.		
			ASTM Test Method
3M tape 5421			
Adhesion to Steel:	34 oz./in. width (37 N/100 mm)		D-3330
Tensile Strength:	46 lbs/in. width (796 N/100 mm)		D-3759
Elongation at Break:	470%		D-3759
Backing Thickness:	5.0 mils (0.13 mm)		D-3652
Total Tape Thickness (without liner):	6.7 mils (0.17 mm)		D-3652
Liner Thickness:	3.5 mils (0.09 mm)		D-3652
Temperature Use Range:	-30° to 225°F (-34° to 107°C)		
3M tape 5423			
Adhesion to Steel:	36 oz./in. width (39 N/100 mm)		D-3330
Tensile Strength:	86 lbs/in. width (1500 N/100 mm)		D-3759
Elongation at Break:	530%		D-3759
Backing Thickness:	10 mils (0.25 mm)		D-3652
Total Tape Thickness (without liner):	12 mils (0.30 mm)		D-3652
Liner Thickness:	3.5 mils (0.09 mm)		D-3652
Temperature Use Range:	-30° to 225°F (-34° to 107°C)		

Features	• Tape demonstrated no evidence of wear through after Taber Abrasion at 1000 cycles, using CS-10 wheel and 1000g load when applied to S-37 mounting sheet. • Low water vapor transmission rate <0.50 g/100in.²/24hrs. • Thick caliper UHMW polyethylene tape for extended service life as a protective surface against tough impact wear or sliding applications. • Outstanding abrasion resistance so will outwear PTFE and other materials in sliding applications. • Low coefficient of friction characteristics is exceeded only by PTFE. • UHMW-PE tape can be used where lubrication is not possible because of contamination. • Rubber Adhesive provides good initial tack for immediate bonding to material surface. • Liner makes it ideal for fabricating or die-cutting into various lengths and shapes.
Application Ideas	• Noise reduction between dissimilar parts. • Reduce squeaks, rattles and other noises that occur with movement • Lining of conveyer guide rails, tank and bin liners, and discharge chutes. • Protection for aluminum sheets on stretch forming presses. • Liners for Spray booths. • Slick surface for easy glide for drawers and cabinets.
Storage	Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% relative humidity in the original packaging material.
Shelf Life	To obtain best performance, use this product within 18 months from date of manufacture.
Technical Information	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.
Product Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method or application.
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9002

This Industrial Adhesives and Tapes Division product was manufactured under a quality system registered to ISO 9001:2000 standards.



Industrial Business
Industrial Adhesives and Tapes Division
 3M Center, Building 220-3S-06
 St. Paul, MN 55144-1000
 3M Company.
 800-362-3550 • 577-369-2923 (Fax)
www.3M.com/industrial

Recycled Paper

*40% pre-consumer
 10% post-consumer*

3M is a trademark of

Printed in U.S.A.
 ©3M 2016

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9