To: **DIGI-KEY CORPORATION**

Issue No. : 151EYG111025742

Date of Issue : 25.Oct.2011

Classification : ■ New □ Changed

PRODUCT SPECIFICATION FOR APPROVAL

Product Description : PGS Graphite Sheet

Product Part Number : EYGA121802DM

Customers Part Number :

Country of Origin : Japan

Applications :

※If you approve this specification, please fill in and sign the below and return 1copy to us.

Approval No :

Approval Date :

Excecuted by :

(signature)

Title :

Dept. :

Circuit Components Business Unit

Panasonic Electronic Devices Co.,Ltd.

1037-2 Kamiosatsu, Chitose City,

Hokkaido 066-8502 Japan

Phone : +81-123-23-8149

Prepared by : Engineering Section

Contact Person :

Signature

Name(Print) : K.KUBO

Title : Engineer

Authorized by :

Signature

Name(Print) : T.Kimura

Title : Manager of Engineering

Panasonic

CLASSIFICATION	SPECIFICATIONS	No. 151S- EYGA121802DM
SUBJE HUAWEI	Part Number	PAGE 1 of 4
PGS Graphite Sheet	EYGA121802DM	25.Oct.2011

1.Scope

This specification applies to Panasonic's PGS Graphite Sheet

2.Explanation of Part Number

Subject : PGS Graphite Sheet

Part Number : EYGA121802DM

E Y G A 1 2 1 8 0 2 D M

- E Y G : Product Code
- A : Form
- 1 2 : Shorter Side (cm)
- 1 8 : Longer Side (cm)
- 0 2 D M : Design Number

Code	Form
S	Sheet
A	Tape attached

3.Operating and storage Temperature Range

Operating Temperature Range : -20 to 100 cels.

Storage Temperature Range : -20 to 80 cels.

4.Performance

4-1.Appearance

Contents	Performance	Test Method
4-1-1 Appearance	There shall be no mechanical scars,tears,hollows which affect the performance	Compared with limit sample
4-1-2 Shape and Dimension	Shown in the figure Page 4 of 4	--

4-2.Initial Performance

Contents	Performance	Test Method
4-2-1 Thermal Diffusivity (PGS)	More than 5.0 cm^2/sec	Test piece;30mm×5mm sheet Testing equipment;"Laser Pit" (The Manufacturer of the Equipment is SINKU-RIKO)

4-3. Reliability Tests (PGS)

Contents	Performance	Test Method
4-3-1 Damp Heat Test	Shall meet the performance prescribed clause 4-1 and 4-2-1	Test temperature : 85±3 cels. Relative humidity : 85±5 %RH Test period : 1000 hours

Circuit Components Business Unit
Panasonic Electronic Devices Co.,Ltd.
1037-2 Kamiosatsu, Chitose City, Hokkaido Japan

APPROVAL	CHECK	DESIGN
T. [illegible]	K. Kubo	K. Kubo

4-3-2 Temperature cycle	Shall meet the performance prescribed clause 4-1 and 4-2-1	Condition the specimen to each temperature from 1 to 4 for the period shown in the table below. Regarding this conditions as one cycle, perform 1000 cycles continuously.
4-3-3 High Temperature Resistance	Shall meet the performance prescribed clause 4-1 and 4-2-1	Test temperature : 100 cels. Test period : 1000 hours
4-3-4 Low Temperature Resistance	Shall meet the performance prescribed clause 4-1 and 4-2-1	Test temperature : -20 cels. Test period : 1000 hours

step	temperature	period(min)
1	-20 cels.	10
2	Room Temp.	3 max.
3	+105 cels.	10
4	Room Temp.	3 max.

5. Packaging

10 sheets of PGS Graphite Sheets shall be put in a plastic bag and the plastic bag shall be sealed. Maximum 25 plastic bags shall be put in an inner carton and a tag on goods specifying Product Name, Part No., Lot No, Quantity shall be put on the top face of the inner carton.
(Max 250 pcs. per inner carton)
Maximum 2 inner cartons shall be put in an outer packaging box and a label specifying Product Name, Part No., Lot No, Quantity (Max 500 pcs.), County of Origin in English shall be put on the side of the outer packaging box.

6. Handling Precautions

6.1 ⚠ Safety Precaution

6.1.1 The PGS shall be used within the specified operating temperature range.
6.1.2 The PGS is soft, do not rub or touch it with rough materials to avoid scratching it.
6.1.3 Lines or folds in the PGS may affect thermal conductivity.
6.1.4 The PGS shall not be used with acid.
The PGS shall not be used in contact with a soldering iron at 400℃ or more.
6.1.5 The PGS shall not be exposed to salt water or direct sunlight during use. The PGS shall not be used in corrosive gases (hydrogen sulfide, sulfurous acid, chlorine, ammonia etc.)
6.1.6 Our PGS has been developed for general industry application. Prior to using the PGS for special applications such as medical, aerospace and aircraft work please contact our engineering staff or the factory.
6.1.7 Never touch a PGS during use because it may be extremely hot.

Note:

6.2 Application notes

6.2.1 Use protective materials when handling and/or applying the PGS, do not use items with sharp edges as they might tear or puncture the PGS.

6.2.2 The PGS dose not work properly if overheated.

6.2.3 Thermal conductivity is dependant on the way it is used.
Test the adaptability of PGS to your application before use.

6.2.4 The PGS has conductivity. If required, the PGS should be provided insulation.

6.2.5 Punching Graphite sheets sends graphite powder; therefore, your check whether or not the graphite powder fall harms devices is necessary.

6.2.6 The PGS shall not be stored under severe conditions of salt water, direct sunlight or corrosive gases (hydrogen sulfide, sulfurous acid, chlorine, ammonia etc.).
The PGS shall not be stored near acid.

7.Substance of this product

7-1 This product not been manufactured with any ozone depleting chemical controlled under the Montreal Protocol.

7-2 This product comply with RoHS(Restriction of the use of certain Hazardous Substance in electrical and electronic equipment) Directive(2002/95/EC).

7-3 All the materials used in this part are registered material under the Law Concerning the Examination and Regulation of Manufacture,etc.of Chemical Substance.

Note:

RevNo	Revision note	Date	Signature	Checked



Notes :

1. All dimensions are millimeters.
2. Materials ; PGS Graphite Sheet
3. Tolerance ; X±3

Itemref	Quantity	Title/Name, designation, material, dimension etc	Article No./Reference
③	1	Polyester tape (0.01mm)(Black)	
②	1	PGS Graphite Sheet (0.017mm)	
①	1	Adhesive tape (0.01mm)	

Design	Check	Approval		Scale
K.KUBO	K.KUBO	T.KIMURA		1 : 2

	Name	Type No.
CIRCUIT COMPONENTS BUSINESS UNIT PANASONIC ELECTRONIC DEVICES CO.,LTD	PGS Graphite Sheet	EYGA121802DM
	Drawing No. 151S-EYGA121802DM	

Общество с ограниченной ответственностью «МосЧип» ИНН 7719860671 / КПП 771901001
Адрес: 105318, г.Москва, ул.Щербаковская д.3, офис 1107

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

http://moschip.ru/get-element

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:
moschip.ru
moschip.ru_4
moschip.ru_6
moschip.ru_9