

Solder Wire Sn99.3/Cu0.7 No-Clean with 2.2% Flux Core 1lb Spool

Product Highlights

No-Clean Water-Washable Synthetic Flux Core

The clear, non-corrosive, non-conductive residue is meant to be left on the board. Residues that do remain are water soluble if you want to remove them. Clean with hot water at 60°C (140°F) minimum.

2.2% flux core

Halogen content: None

RoHS II and REACH compliant

Specifications

| | |
|----------------------|-----------------------------------|
| Alloy: | Sn99.3/Cu0.7 |
| Wire Diameter: | 0.015" (0.38mm) |
| Flux Type: | No-Clean Water-Washable Synthetic |
| Flux Classification: | ROL0 |
| Melting Point: | 227°C (441°F) |
| Packaging: | 1 lb spool |

Test Results

| Test J-STD-004 or other requirements as stated | Test Requirement | Result |
|--|--|--|
| Copper Mirror | IPC-TM-650: 2.3.32 | L: No breakthrough |
| Corrosion | IPC-TM-650: 2.6.15 | L: No corrosion |
| Quantitative Halides | IPC-TM-650: 2.3.28.1 | L: <0.5% |
| Electrochemical Migration | IPC-TM-650: 2.6.14.1 | L: <1 decade drop (No-clean) |
| Surface Insulation Resistance 85°C, 85% RH @ 168 Hours | IPC-TM-650: 2.6.3.7 | L: ≥100MΩ (No-clean) |
| Visual | IPC-TM-650: 3.4.2.5 | Clear and free from precipitation |
| Conflict Minerals Compliance | Electronic Industry Citizenship Coalition (EICC) | Compliant |
| REACH Compliance | Articles 33 and 67 of Regulation (EC) No 1907/2006 | Contains no substance >0.1% w/w that is listed as a SVHC or restricted for use in solder materials |

Conforms to the following Industry Standards:

| | |
|---|-----|
| J-STD-004B, Amendment 1 (Solder Fluxes): | Yes |
| J-STD-006C, Amendments 1 & 2 (Solder Alloys and Fluxed/Non-Fluxed Solders): | Yes |
| RoHS 2 Directive 2011/65/EU: | Yes |

ChipQuik® Solder Wire Orderable Part Numbers:

| Flux Core | Alloy | Melting Point | Diameter | Size | Orderable Part Number | |
|---|-----------|-----------------------|----------------|---------------|-----------------------|-----------------|
| No-Clean Water-Washable Synthetic Flux Core 2.2% (Except .006" and .008" diameter wire which are 1.2%) | Sn63/Pb37 | 183°C (361°F) | .015" (0.38mm) | 100g (3.5oz) | SMDSW.015 100g | |
| | | | | 0.4 oz | SMDSW.020 .4OZ | |
| | | | .020" (0.5mm) | 1 oz | SMDSW.020 1OZ | |
| | | | | 2 oz | SMDSW.020 2OZ | |
| | | | | 4 oz | SMDSW.020 4OZ | |
| | | | | 1/2 lb | SMDSW.020 8OZ | |
| | | | | 1 lb | SMDSW.020 1LB | |
| | | | .031" (0.8mm) | 0.7 oz | SMDSW.031 .7OZ | |
| | | | | 1 oz | SMDSW.031 1OZ | |
| | 2 oz | SMDSW.031 2OZ | | | | |
| | 4 oz | SMDSW.031 4OZ | | | | |
| | 1/2 lb | SMDSW.031 8OZ | | | | |
| | 1 lb | SMDSW.031 1LB | | | | |
| | Sn60/Pb40 | 183-188°C (361-370°F) | .015" (0.38mm) | 100g (3.5oz) | SMD2SW.015 100g | |
| | | | | 0.4 oz | SMD2SW.020 .4OZ | |
| | | | .020" (0.5mm) | 1 oz | SMD2SW.020 1OZ | |
| | | | | 2 oz | SMD2SW.020 2OZ | |
| | | | | 4 oz | SMD2SW.020 4OZ | |
| | | | | 1/2 lb | SMD2SW.020 8OZ | |
| | | | | 1 lb | SMD2SW.020 1LB | |
| | | | .031" (0.8mm) | 0.7 oz | SMD2SW.031 .7OZ | |
| | | | | 1 oz | SMD2SW.031 1OZ | |
| | | | | 2 oz | SMD2SW.031 2OZ | |
| | | | | 4 oz | SMD2SW.031 4OZ | |
| | | | | 1/2 lb | SMD2SW.031 8OZ | |
| | | | | 1 lb | SMD2SW.031 1LB | |
| | | | Sn62/Pb36/Ag2 | 179°C (354°F) | .015" (0.38mm) | 100g (3.5oz) |
| 0.4 oz | | | | | | SMD3SW.020 .4OZ |
| .020" (0.5mm) | 1 oz | SMD3SW.020 1OZ | | | | |
| | 2 oz | SMD3SW.020 2OZ | | | | |
| | 4 oz | SMD3SW.020 4OZ | | | | |
| | 1/2 lb | SMD3SW.020 8OZ | | | | |
| | 1 lb | SMD3SW.020 1LB | | | | |
| .031" (0.8mm) | 0.7 oz | SMD3SW.031 .7OZ | | | | |
| | 1 oz | SMD3SW.031 1OZ | | | | |
| | 2 oz | SMD3SW.031 2OZ | | | | |
| | 4 oz | SMD3SW.031 4OZ | | | | |
| | 1/2 lb | SMD3SW.031 8OZ | | | | |
| | 1 lb | SMD3SW.031 1LB | | | | |

Continued on next page

ChipQuik® Solder Wire Orderable Part Numbers:

Continued from previous page

| Flux Core | Alloy | Melting Point | Diameter | Size | Orderable Part Number |
|---|--------------------|-----------------------|-----------------|-------------------|-----------------------|
| No-Clean Water-Washable Synthetic Flux Core 2.2% (Except .006" and .008" diameter wire which are 1.2%) | Sn96.5/Ag3.0/Cu0.5 | 217-220°C (423-428°F) | .006" (0.15mm) | 50g (1.8oz) | SMDSWLF.006 50g |
| | | | .008" (0.20mm) | 50g (1.8oz) | SMDSWLF.008 50g |
| | | | .015" (0.38mm) | 0.3 oz | SMDSWLF.015 .3OZ |
| | | | | 1 oz | SMDSWLF.015 1OZ |
| | | | | 2 oz | SMDSWLF.015 2OZ |
| | | | | 4 oz | SMDSWLF.015 4OZ |
| | | | | 1/2 lb | SMDSWLF.015 8OZ |
| | | | | 1 lb | SMDSWLF.015 1LB |
| | | | .020" (0.5mm) | 0.4 oz | SMDSWLF.020 .4OZ |
| | | | | 1 oz | SMDSWLF.020 1OZ |
| | | | | 2 oz | SMDSWLF.020 2OZ |
| | | | | 4 oz | SMDSWLF.020 4OZ |
| | | | | 1/2 lb | SMDSWLF.020 8OZ |
| | | | | 1 lb | SMDSWLF.020 1LB |
| | | | .031" (0.8mm) | 0.7 oz | SMDSWLF.031 .7OZ |
| | 1 oz | SMDSWLF.031 1OZ | | | |
| | 2 oz | SMDSWLF.031 2OZ | | | |
| | 4 oz | SMDSWLF.031 4OZ | | | |
| | 1/2 lb | SMDSWLF.031 8OZ | | | |
| | 1 lb | SMDSWLF.031 1LB | | | |
| | Sn99.3/Cu0.7 | 227°C (441°F) | .012" (0.3mm) | 100g (3.5oz) | SMD2SWLF.012 100g |
| | | | .015" (0.38mm) | 0.3 oz | SMD2SWLF.015 .3OZ |
| | | | | 1 oz | SMD2SWLF.015 1OZ |
| | | | | 2 oz | SMD2SWLF.015 2OZ |
| | | | | 4 oz | SMD2SWLF.015 4OZ |
| | | | | 1/2 lb | SMD2SWLF.015 8OZ |
| | | | | 1 lb | SMD2SWLF.015 1LB |
| .020" (0.5mm) | | | 0.4 oz | SMD2SWLF.020 .4OZ | |
| | | | 1 oz | SMD2SWLF.020 1OZ | |
| | | | 2 oz | SMD2SWLF.020 2OZ | |
| | | | 4 oz | SMD2SWLF.020 4OZ | |
| | | | 1/2 lb | SMD2SWLF.020 8OZ | |
| | | | 1 lb | SMD2SWLF.020 1LB | |
| .031" (0.8mm) | | | 0.7 oz | SMD2SWLF.031 .7OZ | |
| | | | 1 oz | SMD2SWLF.031 1OZ | |
| | 2 oz | SMD2SWLF.031 2OZ | | | |
| | 4 oz | SMD2SWLF.031 4OZ | | | |
| | 1/2 lb | SMD2SWLF.031 8OZ | | | |
| | 1 lb | SMD2SWLF.031 1LB | | | |
| Solid Wire (No Flux) | Sn42/Bi57/Ag1 | 138°C (281°F) | .030" (0.762mm) | 32 feet | SMDSWLTLP32 |
| | In100 | 157°C (315°F) | .031" (0.8mm) | 10 feet | SMDIN100 |
| | In52/Sn48 | 118°C (244°F) | .031" (0.8mm) | 10 feet | SMDIN52SN48 |
| | In97/Ag3 | 143°C (289°F) | .031" (0.8mm) | 10 feet | SMDIN97AG3 |

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9