3M[™] Fabric Tape CN-3190 Nickel on Copper-Plated Polyester Fabric

Data Sheet	September 2008
Description	3M [™] Fabric Tape CN-3190 consists of anti-corrosion polyester rip-stop fabric and unique electrically conductive pressure-sensitive acrylic adhesive.
Applications	3M CN-3190 is used in applications typically served by metal foil shielding tapes such as grounding and EMI shielding equipment, components, shielded rooms, etc. The unique metal-plated fabric backing offers the additional benefits of excellent flexibility and conformability, very light weight, and exceptional strength. The fabric backing also minimizes the possibility of finger lacerations.
Shielding Effectiveness	Many factors determine the true shielding effectiveness of a shielding tape, including type and thickness of foil adhesive type, intimacy of contact, smoothness of application surface, strength and frequency of the EMI signal, etc. However, using standard tests and fixtures it is possible to determine a value for the attenuations. For CN-3190 fabric tape, typical shielding effectiveness is in the range of 65dB to 70dB. Before using this product, the user must evaluate it and determine if it is suitable for the intended application.

Typical Properties

Technical information provided consists of typical product data and should not be used for specification purposes. Unless otherwise noted, all tests are performed at room temperature.

Physical

Property (Test Method) (ASTM D1000 unless noted)	Typical Value US units (metric)
Color	Grey
Adhesive	Conductive acrylic
Type of Backing	Copper/Nickel coated ripstop polyester
Total Thickness (backing plus adhesive)	4.3 mils (0,11 mm)
Liner Thickness	5.8 mils (0,14 mm)
Breaking Strength	40 lb/in (18 kgf/25 mm)
Adhesion Strength	31 oz/in (900gf/25 mm)

3M[™] Fabric Tape CN-3190 Nickel on Copper-Plated Polyester Fabric

Typical Properties

Electrical	Property (Test Method) Typical Value			
	(ASTM D1000 unless noted)	US units (metric)		
	Electrical Resistance Through Adhesive ¹	0.05 ohms		
	¹ MIL-STD-202 Method 307 maintained at 5 psi (3,4 N/cm2) measured over 1 in 2 surface area. Conductive particles in the adhesive provide the electrical path between the application substrate and the foil backing.			
Specifications	 Anti-corrosion treated Cu/Ni conductive fabric Conductive acrylic adhesive 			
	 Supplied on a removable liner for easy handling and die cutting 			
Shelf Life & Storage	The tape has a 5-year shelf life from date of manufacture when stored in a clean, dry place at a temperature of 70° F (21° C) and 40-50% relative humidity.			
Availability	For availability, please contact your local distributor. Names and addresses are available from 3M.com/electrical [Where to Buy] or call 1-800-676-8381.			
Important Notice	All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.			
Warranty; Limited Remedy; Limited Liability	This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHAN OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.			

3M is a trademark of 3M Company.



Electrical Markets Division 6801 River Place Blvd. Austin, TX 78726-9000 800 676 8381 FAX 800 828 9329 www.3M.com/electrical/oem

Please recycle. © 3M 2008 All rights reserved. 78-8126-9843-5_B





Общество с ограниченной ответственностью «МосЧип» ИНН 7719860671 / КПП 771901001 Адрес: 105318, г.Москва, ул.Щербаковская д.З, офис 1107

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

http://moschip.ru/get-element

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж: moschip.ru moschip.ru_4

moschip.ru_6 moschip.ru_9