



WonderMASK P Peelable Solder Mask

Product# 2211

Product Description

WonderMASK P is a temporary, peel-able solder mask comprised of a thixotropic, synthetic acrylic latex designed to withstand fluxing, wave soldering and cleaning operations. Unlike natural latex mask, it contains no offensive ammonia and hence is non-corrosive to copper, gold, silver or pre-soldered surfaces. In addition, stability problems are averted. When applied, the product is opaque pink, and when cured, becomes completely translucent red. Cured mask can be used for masking conformal coatings. May be used in applications such as robotic, pneumatic, hand applied or template screening (not recommended for silk screening).

Techspray's WonderMASK is the industry-leading temporary solder mask brand because of quality and versatility. Depending on the product, mask can be peeled off manually or washed off in a batch or inline system.

WonderMASK has a number of useful applications in PCB assembly:

- Thru-hole masking – Prevent soldering open holes in a wave soldering process by covering with WonderMASK. All of the masks listed below are well suited for this application.
- Conformal coating masking – In a conformal coating dipping or spraying process, WonderMASK can be used to cover connectors and other components and areas that should not be coated.
- Temporary component adhesive – WonderMASK can be used to tack down components on double-sided PCBs.

All Techspray WonderMASK products have the following advantages:


- Can be cured in pre-heat
- Withstands lead-free soldering temperatures up to 640°F (343°C) in wave soldering process
- RoHS compliant

Features / Benefits

- Non-ammoniated
- Nonflammable
- Easily peel-able
- Low odor
- Cure indicator - darkens as it cures
- Compatible with gold and copper leads

Usage Instructions

Apply a 20 to 30 mil coating for best results to desired area. The substrate should be free from flux, oil, and particulate matter. Drying times depend upon ambient humidity. Under normal conditions WonderMASK P is ready for preheating stage in 1 hour, however, cure can be accelerated to 30 minutes at 65°C/150°F or 20 minutes at 82°C/180°F. Do not over cure, as blistering of mask can occur, causing removal problems. Mask will change from an opaque pink to a translucent red when complete cure is accomplished. Mask does not have to be completely dry to withstand soldering operation; however, it should be completely translucent before removal.



Typical Product Data and Physical Properties

Physical state:	Liquid
Color:	Pink/red
Relative density:	1
Shelf life:	2 years

Performance & Application Data

Application	Template, hand, pneumatic, robotic
Viscosity	28,000-30,000 cps
Suggested thickness	20-30 mils
Thinner	DI water
Cure time	1hr. Ambient, 30 min. @65°C, 20 min. @82°C
Removal	Peel-able

WonderMASK P Peelable Solder Mask

Product# 2211

Packaging and Availability

2211-8SQ	8 oz. Liquid
2211-G	1 Gallon Liquid
2211-5G	5 Gallon Liquid
2211-54G	54 Gallon Liquid

Environmental Policy

Techspray® is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

Resources

Techspray® products are supported by global sales, technical and customer services resources.

For additional technical information on this product or other Techspray® products in the United States, call the technical sales department at 800-858-4043, email tsales@techspray.com or visit our web site at: www.techspray.com.

Important Notice to Purchaser/User: The information in this publication is based on tests that we believe are reliable. The results may vary due to differences in tests type and conditions. We recommend that each user evaluate the product to determine its suitability for the intended application. Conditions of use are outside our control and vary widely. Techspray's only obligation and your only solution is replacement of product that is shown to be defective when you receive it. In no case will Techspray® be liable for any special, incidental, or consequential damages based on breach of warranty, negligence or any other theory.

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9