

RF CONDUCTIVE CAULKING COMPOUND AND SEALER



Eccoshield VY-81 is a single-component electrically conductive non-hardening compound of metallic particles. It is similar to but different from our Eccoshield® VY product, in that the VY-81 has an increased volume resistivity (decreased conductivity). It also has a lower density than Eccoshield VY and is more cost effective to use per pound. Once applied, Eccoshield VY-81 assures long-term integrity of the shielding enclosure and will prevent corrosion in the contact area. Due to high tack and non-hardening characteristics, Eccoshield VY-81 will function under vibration and displacement due to temperature changes. It is fast and economical to use.

FEATURES AND BENEFITS

- maintains good shielding effectiveness due to non-hardening characteristic of material
- material can be applied using conventional caulking equipment

MARKETS

- Commercial Telecom
- Test and Measurement
- Security and Defense

SPECIFICATIONS

TYPICAL PROPERTIES	ECCOSHIELD VY-81
Service Temperature °C (°F)	-54 to 205 (-65 to 400)
Volume Resistivity Ohm-cm	0.01
Density g/cc	1.80
Shielding effectiveness dB	80 - 90
Length of 3mm diam. bead/lb, m (ft)	32 (105)

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

APPLICATIONS

- Eccoshield VY-81 is specifically designed for use as a shielding effective material for EMI/RF protection on structures, cabinets, conduits, modules and components.
- Joints, seams, threads, cracks, and other RF leakage sources can be effectively plugged.

AVAILABILITY

- Eccoshield VY-81 is sold by the pound in one pound (16 oz.) jars.

INSTRUCTIONS FOR USE

- Eccoshield VY-81 can be used with conventional caulking equipment to develop fast and uniform-weight beads. It can also be applied by spatula, putty knife, plastic syringe applicators, or other suitable tools such as caulking guns. For spatula application, small amount of methyl ethyl ketone (MEK) can be added to adjust consistency.
- All surfaces for application should be prepared by removing rust, scale, non-conductive oxides and dirt. Wire brushing and/or solvent cleaning is usually adequate. Surfaces should be bright and electrically conductive.

- Apply Eccoshield VY-81 to the prepared surface using a syringe, caulking gun, or spatula. Lap joints may be made immediately. Excess and spillage may be collected and reused. Hardened or thick material can be reactivated by the addition of small amounts of methyl ketone.
- For cleanup, acetone or trichloroethylene are suitable.

Caution: Eccoshield VY-81 contains flammable solvents. Keep away from heat and open flames. When not in use, keep sealed to avoid evaporation. The handling of these products should present no problems if ordinary care is exercised to avoid breathing vapors, the skin is protected against contamination, swallowing is avoided, and eyes are protected.

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9