

3M Anisotropic Conductive Film (ACF)
Interconnect Solutions



Get Connected



3M

Get Connected with 3M™ Anisotropic Conductive Film (ACF)

3M offers you a variety of high-performance anisotropic conductive adhesive products, used to mechanically and electrically connect flex circuits to a variety of substrates.

These reliable, production-proven technologies can replace soldering and mechanical fasteners in many applications, reducing assembly time and saving on space requirements.


Get the job done faster, easier and more economically with 3M™ Anisotropic Conductive Film (ACF) Interconnect Solutions

- Products for a variety of applications
 - Flex circuit to PCB
 - Flex circuit to flex circuit
 - Flex circuit to glass panels
- Good room temperature stability for long life on the factory floor
- Low temperature processing for lead free solutions
- Replaces connectors for cost savings, lower Z-axis standoff

Choose the 3M ACF Adhesive That's Right for Your Application

	Flex-On-Board			Flex-On-Glass
	3M ACF 5363	3M ACF 7303	3M ACF 7378	3M ACF 5552
Adhesive Thickness (micron)	40	75	40	19
Particle Diameter (micron)	10	43	10	6
Type of Particle	Au/Ni	Ag/Glass	Au/Ni	Au/Ni/Polymer
Bonding Temperature (°C)	195 to 210	135 to 150	160 to 180	170 to 190
Bonding Time (seconds)	10 to 20	25	5 to 9	20 to 30
Bonding Pressure (MPa)	3 to 5	2	3 to 4	2 to 4
Minimum Pitch (micron)	200	500	200	<100
Minimum Pad Area (mm ²)	0.15	0.75	0.2	0.015
Connection Resistance	<100 mOhms	<200 mOhms	<100 mOhms	<20 Ohms
90° Peel Adhesion (g/cm)	>700	>500	>1000	>800
Temp/Humidity Aging (°C/%r.h.)	85/85	70/90	85/85	85/85
Temp Cycling (°C)	-40 to 100	-40 to 80	-40 to 85	-40 to 100
Flex Type				
Silver Ink on Polyester		X		
Gold/Copper on Polyester		X	X	
Gold/Copper on Polyimide	X	X	X	X
Connection Type				
Flex to Glass		X ¹		X
Flex to Plastic Device		X ²		
Flex to PC Board	X	X	X	
Flex to Flex	X	X	X	X

¹Tested only for silver frit; not suitable for ITO traces. ²Suitable for silver ink traces only; not suitable for ITO traces.



Adhesive Technologies

3M™ Anisotropic Conductive Film (ACF) Adhesives

Heat-bondable 3M™ ACF films, consisting of thermoplastic and thermoset adhesives randomly loaded with conductive particles. These particles allow interconnection of circuit lines through the adhesive thickness, but are spaced far enough apart for the product to be electrically insulating along the plane of the adhesive.

ss	Flex-On-PET/Glass	Flex-On-PET	Camera Module	Camera Module Flex-On-PET
R	3M ACF 7371	3M ACF 7393	3M ACF 7376-10	3M ACF 7376-20
	25	25	40	35
	10	10	10	20
	Au/Ni/Polymer	Au/Ni/Polymer	Au/Ni/Polymer	Au/Ni/Polymer
	140 to 170	150 to 170	140 to 160	140 to 160
	10 to 15	10 to 20	7 to 15	7 to 15
	1 to 2	1 to 2	1 to 2	1 to 2
	200	200	200	500
	0.2	0.2	0.2	0.5
	<100 mOhms	<100 mOhms	<100 mOhms	<100 mOhms
	>700	>700	>700	>700
	85/85	70/90	85/85	85/85
	-40 to 85	-20 to 60	-40 to 85	-40 to 85
	X	X	X	X
	X	X	X	X
	X	X	X	X
	X	X		
	X	X		X
			X	X
	X	X	X	X






3M™ Electrically Conductive Adhesive Transfer Tape (ECATT)

An easy-to-use, pressure sensitive tape designed for connecting, bonding and grounding flex circuits, PCBs and EMI/RFI shields and gaskets. Applied at room temperature – no thermal bonding required! Not recommended for extreme high or low temperatures.

	3M ECATT 9703	3M ECATT 9705
Adhesive Thickness (micron)	50	50
Type of Particle	Ag/Ni	Ag/Ni
Pitch (micron)	800	800
Application Notes	Good adhesion; reworkable. For connecting/bonding/grounding flex circuits, printed circuits boards, EMI/RFI shields & gaskets, PSA attachments at room temp. Not recommended for extreme high/low temps.	



Contact 3M

3M provides applications development support. For more information, contact 3M at 800-251-8634. Or visit us on the web: www.3M.com/electronics.

Product Use: All statements, technical information and recommendations contained in this document are based on tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy: Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation Of Liability: Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental, or consequential regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Electronics Markets Materials Division 3M Electronics

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
www.3M.com/electronics
1-800-251-8634

Please recycle. Printed in USA.
Issued: 5/09 © 3M 2009.
All rights reserved. 6859HB
60-5002-0057-5

3M is a trademark of 3M Company.
Used under license by 3M subsidiaries and affiliates.

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9