

Doc. Number: TTDS-240

Issue: 2

Date: February 2014

Page **1** of **3**

DATASHEET

HXCT Continuous Tubing

HXCT continuous tubing is a thin walled, zero halogen, low smoke, low toxicity, radiation cross-linked polyolefin heat shrinkable marker sleeve. The marker sleeve is supplied on spools and is printed and cut/perforated to the desired length using the printer systems referenced.

Material

The sleeving shall be fabricated from irradiated, thermally stabilised and flame retarded modified polyolefin compound containing no halogens or cadmium in the formulation.

Dimensions

Part Description	Supplied ID mm (in)	Recovered ID mm (in)	Recovered wall nominal. mm (in)
HXCT-2.4	2.4 (0.094)	1.19 (0.047)	0.50 (0.02)
HXCT-3.2	3.2 (0.126)	1.6 (0.063)	0.50 (0.02)
HXCT-4.8	4.8 (0.189)	2.4 (0.094)	0.51 (0.02)
HXCT-6.4	6.4 (0.250)	3.2 (0.126)	0.65 (0.026)
HXCT-9.5	9.5 (0.375)	4.8 (0.189)	0.65 (0.026)
HXCT-12.7	12.7 (0.500)	6.4 (0.250)	0.65 (0.026)
HXCT-19.0	19.0 (0.750)	9.5 (0.375)	0.75 (0.030)
HXCT-25.4	25.4 (1.0)	12.7 (0.50)	0.90 (0.035)
HXCT-38.1	38.1 (1.5)	19.1 (0.75)	1.00 (0.039)

Print System

The recommended Printer Ribbon Systems for use with HXCT are shown in the latest version of document 411-121005 Identification Printer Product Ribbon Matrix

While TE Connectivity has made every reasonable effort to ensure the accuracy of the information in this specification, TE Connectivity does not guarantee that it is error-free, nor does TE Connectivity make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. TE Connectivity reserves the right to make any adjustments to the information contained herein at any time without notice. TE Connectivity expressly disclaims all implied warranties regarding the information contained herein, including, but not limited to, any implied warranties of merchantability or fitness for a particular purpose. The dimensions in this document are for reference purposes only and are subject to change without notice. Specifications are subject to change without notice. Consult TE Connectivity for the latest dimensions and design specifications.



Doc. Number: TTDS-240

Issue: 2

Date: February 2014

Page 2 of 3

DATASHEET

HXCT Continuous Tubing

PROPERTIES

Adherence of Marking

Print legible after 50 rubs

RW-2072 Clause 3.8.1 (In accordance with SAE-AS5942)

Fluid Resistance

IRM902 MIL-PRF-23699 Skydrol LD-4

MIL-H-83282

JP-8 24 hour total immersion at 24°± 3°C Print legible after after 20 wipes

RW-2072 Clause 3.8.2 (in accordance with SAE AS 5942)

Diesel Fuel Propylene Glycol de-icing

fluid 50/50 Tap water

5% Sodium chloride solution

1% Teepol

Saturated cloth wipe

RW-2072 Clause 3.8.2 (in accordance with SAE AS 5942)

HCL 5% solution NaOH 5% solution

Isopropyl alcohol

1min. at 23°C, 10 wipes – C8¹ min. 1min. at 23°C, 10 wipes – C8¹ min.

RW-2072 Clause 3.8.2 (in accordance with SAE AS 5942)

IRM 902 oil

70hrs. at 50°C. Print legible after 10 wipes

Mandrel bend:

RW-2072 Clause 3.8.2 (in accordance with SAE AS 5942)

Thermal Properties

Heat Shock 240min at 175°C

Mandrel bend: No dripping flowing or cracking Print legible after 20 rubs

RW-2072 Clause 3.3.2 (in accordance with ASTM D2671)

Heat Ageing

No dripping flowing or cracking 168hrs at 135°C Print legible after 20 rubs No cracking

RW-2072 Clause 3.3.1 (in accordance with ASTM D2671)

Low Temperature Bend

240min at -55°C

RW-2072 Clause 3.3.4 (in accordance with IEC 60684-2)

Electrical Properties

Dielectric Strength

15 MV/m minimum

RW-2072 Clause 3.4.1 (in accordance with ASTM D2671)

Volume Resistivity After Damp Heat

 $10^{12}\,\Omega$ cm minimum

RW-2072 Clause 3.4.2 (in accordance with ASTM D2671)

©2014 Tyco Electronics Corporation, a TE Connectivity Ltd. Company

TTDS-240 Issue 2



Doc. Number: TTDS-240

Issue: 2

Date: February 2014

Page 3 of 3

DATASHEET

HXCT Continuous Tubing

ame Properties		
Flammability	Self Extinguishing	RW-2072 Clause 3.7.1 (ASTM D2671 Procedure B)
Oxygen Index (OI)	34% minimum	RW-2072 Clause 3.7.2 EN 45545-2 (EN ISO 4589-2:1999,
Dripping Classification	Classification ST2	RW-2072 Clause 3.7.11 (DIN 5510-2)
Smoke Density	0.017 maximum	RW-2072 Clause 3.7.7 (BS 6853:1999 Annex D.8.3)
Smoke	20 maximum Smoke class F1	RW-2072 Clause 3.7.4 (ASTM E662)
LUL Toxic Fume	No Halogens, -P, -S, -N sources above trace levels	RW -2072 Clause 3.7.8
er Properties		
opper Mirror Corrosion: 16 hours at 150°C	No corrosion of mirrors above 8%	RW-2072 Clause 3.5.1 (ASTM D2671)
Water Absorption: 24hrs at 23°C	1.0% maximum	RW-2072 Clause 3.5.2 (ASTM D570)
UV Resistance	Mandrel bend test Print legible after 20 rubs	RW-2072 Clause 3.6.1 (ASTM G154)

Product is compliant to EU RoHS Directive 2002/95/EC. This compliance information is provided based on reasonable inquiry of our suppliers and represents our current actual knowledge based on the information provided by our suppliers. This information is subject to change

ПОСТАВКА ЭЛЕКТРОННЫХ КОМПОНЕНТОВ

Общество с ограниченной ответственностью «МосЧип» ИНН 7719860671 / КПП 771901001 Адрес: 105318, г.Москва, ул.Щербаковская д.3, офис 1107

Данный компонент на территории Российской Федерации Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

http://moschip.ru/get-element

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г. Москва, ул. Щербаковская д. 3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru moschip.ru_6 moschip.ru_4 moschip.ru_9