

MICROLITE[®] Toroidal Cores are manufactured with Metglas[®] amorphous alloy 2605SA1 ribbon. Their unique combination of high saturation flux density and low loss make them the first choice for all energy storage applications, enabling the designer to achieve both size and system cost reduction.



Applications

- SMPS output inductors
- Flyback transformers
- Differential input inductors
- PVC inductors
- VRM inductors

Benefits

- High saturated flux density
- Significant size reduction
- Low core loss
- Extended bias capability
- Fewer turns due to higher permeability

Physical Properties Metglas MICROLITE XP Cores

| | |
|---|------|
| Ribbon Thickness (μm) | .23 |
| Density (g/cm ³) | 7.18 |
| Thermal Expansion (ppm/°C) | 7.6 |
| Crystallization Temperature (°C) | .508 |
| Curie Temperature (°C) | .399 |
| Continuous Service Temperature (°C) | .150 |

Magnetic Properties Metglas MICROLITE XP Cores

| | |
|---|----------|
| Saturation Flux Density (T) | 1.56 |
| Permeability (depending on core size) | .245/270 |

Percent Permeability vs. DC Bias @ 25°C

MICROLITE $\mu = 245$



MICROLITE $\mu = 270$



Core Loss vs. Flux Density @ 25°C



Temperature Dependence of Inductance

MICROLITE $\mu = 245$



Permeability vs. Frequency





Ordering Information

Example:
MP1710XDGC

METGLAS Products
Outside Diameter (OD)
Height (HT)

Distributed Gap Core

| Box Type (X) | DuPont Material | UL File No. | Flam. Rating UL 94 | Elec. Rel. Temp. Rec. Index (UL746B) Temp. |
|--------------|-----------------|-------------|--------------------|--|
| P | Zyrel® 7DG33L | E41938 | HB | 120 |
| L | Zyrel® FR50 | E41938 | V-0 | 130 |
| V | Rymite® FR530L | E68678 | V-0 | 150 |
| M | Epoxy FR534SD | E206120 | — | — Class B, F |

Encapsulated cores are available upon request.

| MICROLITE® Toroidal Cores | | | | | | | | | | |
|---------------------------|----------------|--------------|--------------|------------------------|-----------------------------------|------------------------|-----------------------------------|--|--------------|---------------------------------------|
| Core No. | CORE DIMENSION | | | Performance Parameters | | | | | | |
| | O.D.Max (mm) | I.D.Min (mm) | Ht. Max (mm) | l _m (cm) | A _c (cm ²) | Vol (cm ³) | W _a (cm ²) | W _a A _c (cm ⁴) | Initial Perm | A _L * (nH/N ²) |
| MP1005MDGC | 11.32 | 4.47 | 6.12 | 2.40 | 0.10 | 0.25 | 0.16 | 0.016 | 270 | 144.1 |
| MP1105MDGC | 12.19 | 6.07 | 6.29 | 2.80 | 0.10 | 0.27 | 0.29 | 0.028 | 270 | 116.5 |
| MP1205MDGC | 13.66 | 7.46 | 6.29 | 3.22 | 0.09 | 0.30 | 0.44 | 0.041 | 270 | 97.7 |
| MP1306MDGC | 14.67 | 7.46 | 7.87 | 3.37 | 0.15 | 0.51 | 0.44 | 0.066 | 245 | 137.8 |
| MP1603MDGC | 17.03 | 8.99 | 4.70 | 3.98 | 0.09 | 0.34 | 0.63 | 0.055 | 270 | 73.9 |
| MP1710MDGC | 18.68 | 12.16 | 11.05 | 4.74 | 0.20 | 0.94 | 1.16 | 0.230 | 245 | 128.5 |
| MP2010MDGC | 21.25 | 12.16 | 11.05 | 5.13 | 0.30 | 1.54 | 1.16 | 0.348 | 245 | 180.1 |
| MP2310MDGC | 24.35 | 12.16 | 11.05 | 5.60 | 0.43 | 2.38 | 1.16 | 0.494 | 245 | 233.7 |
| MP2510MDGC | 26.84 | 18.51 | 11.05 | 7.01 | 0.27 | 1.89 | 2.69 | 0.725 | 245 | 118.4 |
| MP2610MDGC | 26.92 | 15.97 | 11.05 | 6.61 | 0.37 | 2.48 | 2.00 | 0.751 | 245 | 174.6 |
| MP3210MDGC | 33.57 | 21.69 | 11.05 | 8.54 | 0.41 | 3.52 | 3.69 | 1.520 | 245 | 148.3 |
| MP3310MDGC | 34.06 | 14.70 | 11.05 | 7.49 | 0.71 | 5.34 | 1.70 | 1.210 | 245 | 292.9 |
| MP3505MDGC | 36.40 | 21.69 | 6.29 | 8.97 | 0.26 | 2.35 | 3.69 | 0.968 | 245 | 90.0 |
| MP3510MDGC | 36.52 | 18.51 | 11.05 | 8.48 | 0.66 | 5.58 | 2.69 | 1.770 | 245 | 238.9 |
| MP3710MDGC | 38.50 | 21.69 | 11.05 | 9.29 | 0.61 | 5.66 | 3.69 | 2.251 | 245 | 201.9 |
| MP4010MDGC | 41.58 | 21.69 | 11.05 | 9.76 | 0.73 | 7.15 | 3.69 | 2.706 | 245 | 231.1 |
| MP4510MDGC | 46.73 | 21.69 | 11.05 | 10.55 | 0.94 | 9.91 | 3.69 | 3.472 | 245 | 274.4 |
| MP7050MDGC | 13.23 | 7.46 | 6.12 | 3.14 | 0.08 | 0.25 | 0.44 | 0.035 | 245 | 78.2 |
| MP7089MDGC | 46.55 | 28.95 | 15.72 | 11.65 | 0.94 | 10.92 | 6.58 | 6.170 | 245 | 247.7 |
| MP7109MDGC | 57.21 | 37.44 | 15.32 | 14.64 | 1.03 | 15.13 | 11.01 | 11.376 | 245 | 217.4 |
| MP7120MDGC | 17.31 | 10.46 | 7.87 | 4.24 | 0.14 | 0.59 | 0.86 | 0.119 | 245 | 100.3 |
| MP7195MDGC | 54.32 | 26.97 | 16.52 | 12.49 | 1.60 | 19.98 | 5.71 | 9.136 | 245 | 394.1 |
| MP7206MDGC | 21.41 | 13.46 | 7.87 | 5.35 | 0.17 | 0.89 | 1.42 | 0.238 | 245 | 96.2 |
| MP7254MDGC | 39.38 | 24.86 | 15.65 | 9.91 | 0.75 | 7.46 | 4.85 | 3.656 | 245 | 234.1 |
| MP7310MDGC | 23.49 | 13.46 | 7.87 | 5.66 | 0.22 | 1.25 | 1.42 | 0.315 | 245 | 120.7 |
| MP7324MDGC | 36.99 | 23.01 | 11.05 | 9.24 | 0.49 | 4.50 | 4.16 | 2.026 | 245 | 162.3 |
| MP7350MDGC | 23.53 | 14.22 | 9.91 | 5.79 | 0.27 | 1.55 | 1.59 | 0.425 | 245 | 142.3 |
| MP7380MDGC | 18.30 | 10.23 | 7.87 | 4.35 | 0.17 | 0.74 | 0.82 | 0.140 | 245 | 120.6 |
| MP7438MDGC | 46.61 | 25.22 | 18.99 | 11.05 | 1.43 | 15.80 | 4.99 | 7.141 | 245 | 398.4 |
| MP7548MDGC | 33.25 | 19.73 | 11.05 | 8.15 | 0.47 | 3.82 | 3.06 | 1.435 | 245 | 177.4 |
| MP7585MDGC | 34.87 | 23.95 | 9.91 | 9.08 | 0.32 | 2.93 | 4.50 | 1.452 | 245 | 109.3 |
| MP7715MDGC | 51.53 | 32.46 | 13.89 | 12.97 | 0.89 | 11.57 | 8.27 | 7.379 | 245 | 211.7 |
| MP7930MDGC | 27.18 | 13.46 | 11.05 | 6.21 | 0.48 | 2.97 | 1.42 | 0.681 | 245 | 237.3 |

| MICROLITE® Toroidal Cores | | | | | | | | | | |
|---------------------------|----------------|--------------|--------------|------------------------|-----------------------------------|------------------------|-----------------------------------|--|--------------|---------------------------------------|
| Core No. | CORE DIMENSION | | | Performance Parameters | | | | | | |
| | O.D.Max (mm) | I.D.Min (mm) | Ht. Max (mm) | l _m (cm) | A _c (cm ²) | Vol (cm ³) | W _g (cm ²) | W _g A _c (cm ⁴) | Initial Perm | A _L * (nH/N ²) |
| MP1306LDGC | 15.80 | 6.17 | 8.13 | 3.37 | 0.15 | 0.51 | 0.30 | 0.045 | 245 | 137.8 |
| MP1306PDGC | 15.80 | 6.17 | 8.13 | 3.37 | 0.15 | 0.51 | 0.30 | 0.045 | 245 | 137.8 |
| MP1306VDGC | 15.80 | 6.17 | 8.13 | 3.37 | 0.15 | 0.51 | 0.30 | 0.045 | 245 | 137.8 |
| MP1603LDGC | 18.24 | 7.87 | 4.70 | 3.98 | 0.09 | 0.34 | 0.49 | 0.042 | 270 | 73.9 |
| MP1603PDGC | 18.24 | 7.87 | 4.70 | 3.98 | 0.09 | 0.34 | 0.49 | 0.042 | 270 | 73.9 |
| MP1603VDGC | 18.24 | 7.87 | 4.70 | 3.98 | 0.09 | 0.34 | 0.49 | 0.042 | 270 | 73.9 |
| MP1710LDGC | 20.22 | 10.87 | 11.43 | 4.74 | 0.20 | 0.94 | 0.93 | 0.184 | 245 | 128.5 |
| MP1710PDGC | 20.22 | 10.87 | 11.43 | 4.74 | 0.20 | 0.94 | 0.93 | 0.184 | 245 | 128.5 |
| MP1710VDGC | 20.22 | 10.87 | 11.43 | 4.74 | 0.20 | 0.94 | 0.93 | 0.184 | 245 | 128.5 |
| MP2010LDGC | 22.78 | 10.87 | 11.43 | 5.13 | 0.30 | 1.54 | 0.93 | 0.278 | 245 | 180.1 |
| MP2010PDGC | 22.78 | 10.87 | 11.43 | 5.13 | 0.30 | 1.54 | 0.93 | 0.278 | 245 | 180.1 |
| MP2010VDGC | 22.78 | 10.87 | 11.43 | 5.13 | 0.30 | 1.54 | 0.93 | 0.278 | 245 | 180.1 |
| MP2310LDGC | 25.91 | 10.80 | 11.48 | 5.60 | 0.43 | 2.38 | 0.92 | 0.389 | 245 | 233.7 |
| MP2310PDGC | 25.91 | 10.80 | 11.48 | 5.60 | 0.43 | 2.38 | 0.92 | 0.389 | 245 | 233.7 |
| MP2310VDGC | 25.91 | 10.80 | 11.48 | 5.60 | 0.43 | 2.38 | 0.92 | 0.389 | 245 | 233.7 |
| MP2510LDGC | 27.79 | 17.27 | 11.48 | 7.01 | 0.27 | 1.89 | 2.34 | 0.631 | 245 | 118.4 |
| MP2510PDGC | 27.79 | 17.27 | 11.48 | 7.01 | 0.27 | 1.89 | 2.34 | 0.631 | 245 | 118.4 |
| MP2510VDGC | 27.79 | 17.27 | 11.48 | 7.01 | 0.27 | 1.89 | 2.34 | 0.631 | 245 | 118.4 |
| MP2610LDGC | 28.32 | 14.15 | 11.48 | 6.61 | 0.37 | 2.48 | 1.57 | 0.589 | 245 | 174.6 |
| MP2610PDGC | 28.32 | 14.15 | 11.48 | 6.61 | 0.37 | 2.48 | 1.57 | 0.589 | 245 | 174.6 |
| MP2610VDGC | 28.32 | 14.15 | 11.48 | 6.61 | 0.37 | 2.48 | 1.57 | 0.589 | 245 | 174.6 |
| MP3210LDGC | 34.95 | 19.86 | 11.48 | 8.54 | 0.41 | 3.52 | 3.10 | 1.275 | 245 | 148.3 |
| MP3210PDGC | 34.95 | 19.86 | 11.48 | 8.54 | 0.41 | 3.52 | 3.10 | 1.275 | 245 | 148.3 |
| MP3210VDGC | 34.95 | 19.86 | 11.48 | 8.54 | 0.41 | 3.52 | 3.10 | 1.275 | 245 | 148.3 |
| MP3310LDGC | 36.07 | 12.95 | 11.48 | 7.49 | 0.71 | 5.34 | 1.32 | 0.939 | 245 | 292.9 |
| MP3310PDGC | 36.07 | 12.95 | 11.48 | 7.49 | 0.71 | 5.34 | 1.32 | 0.939 | 245 | 292.9 |
| MP3310VDGC | 36.07 | 12.95 | 11.48 | 7.49 | 0.71 | 5.34 | 1.32 | 0.939 | 245 | 292.9 |
| MP3510LDGC | 38.10 | 16.69 | 11.48 | 8.48 | 0.66 | 5.58 | 2.19 | 1.439 | 245 | 238.9 |
| MP3510PDGC | 38.10 | 16.69 | 11.48 | 8.48 | 0.66 | 5.58 | 2.19 | 1.439 | 245 | 238.9 |
| MP3510VDGC | 38.10 | 16.69 | 11.48 | 8.48 | 0.66 | 5.58 | 2.19 | 1.439 | 245 | 238.9 |
| MP4010LDGC | 43.05 | 19.86 | 11.48 | 9.76 | 0.73 | 7.15 | 3.10 | 2.270 | 245 | 231.1 |
| MP4010PDGC | 43.05 | 19.86 | 11.48 | 9.76 | 0.73 | 7.15 | 3.10 | 2.270 | 245 | 231.1 |
| MP4010VDGC | 43.05 | 19.86 | 11.48 | 9.76 | 0.73 | 7.15 | 3.10 | 2.270 | 245 | 231.1 |
| MP4510LDGC | 48.13 | 19.86 | 11.48 | 10.55 | 0.94 | 9.91 | 3.10 | 2.912 | 245 | 274.4 |
| MP4510PDGC | 48.13 | 19.86 | 11.48 | 10.55 | 0.94 | 9.91 | 3.10 | 2.912 | 245 | 274.4 |
| MP4510VDGC | 48.13 | 19.86 | 11.48 | 10.55 | 0.94 | 9.91 | 3.10 | 2.912 | 245 | 274.4 |

Contact Information:

AMERICAS

Hitachi Metals America Ltd.

2101 S. Arlington Hts. Rd., Ste. 116
Arlington Heights, IL
60005-4142

Tel: (847) 364-7200 ext. 8219

Fax: (847) 364-7279 Fax

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9