3M ATG Tape 987

Technical Data		June, 2004
Product Description	3M [™] ATG Tape 987 is a generation and various foams.	eral purpose tape for holding many paper, foils, films
Construction	Adhesive Type:	400 Acrylic*
	Release Liner:	Tan Densified Kraft Paper
	Approximate Thickness: Release Liner:	.0035 in. (0.09 mm)
	Tape Only:	.0017 in. (0.040 mm)
	Tape Color:	Clear
Typical Physical		nformation and data should be considered representative
	or typical only and shoul Adhesion to Steel:	d not be used for specification purposes.
Properties and Performance	or typical only and shoul	
Properties and Performance	or typical only and shoul Adhesion to Steel: (ASTM D3330) Relative High Temperature Operating Ranges:	d not be used for specification purposes. 20 oz./in. width (22 N/100 mm)
Properties and Performance	or typical only and shoul Adhesion to Steel: (ASTM D3330) Relative High Temperature Operating Ranges: Long term: (days, weeks)	d not be used for specification purposes. 20 oz./in. width (22 N/100 mm) 250°F (121°C)
Properties and Performance	or typical only and shoul Adhesion to Steel: (ASTM D3330) Relative High Temperature Operating Ranges: Long term: (days, weeks) Short term: (minutes, hours)	20 oz./in. width (22 N/100 mm) 250°F (121°C) 180°F (82°C)
Properties and Performance Characteristics	or typical only and shoul Adhesion to Steel: (ASTM D3330) Relative High Temperature Operating Ranges: Long term: (days, weeks) Short term: (minutes, hours) Relative Solvent Resistance:	d not be used for specification purposes. 20 oz./in. width (22 N/100 mm) 250°F (121°C) 180°F (82°C) Good
Properties and Performance Characteristics	or typical only and shoul Adhesion to Steel: (ASTM D3330) Relative High Temperature Operating Ranges: Long term: (days, weeks) Short term: (minutes, hours) Relative Solvent Resistance: UV Resistance: Available Lengths:	d not be used for specification purposes. 20 oz./in. width (22 N/100 mm) 250°F (121°C) 180°F (82°C) Good Excellent
Properties and Performance	or typical only and shoul Adhesion to Steel: (ASTM D3330) Relative High Temperature Operating Ranges: Long term: (days, weeks) Short term: (minutes, hours) Relative Solvent Resistance: UV Resistance: UV Resistance: Available Lengths: Standard	d not be used for specification purposes. 20 oz./in. width (22 N/100 mm) 250°F (121°C) 180°F (82°C) Good Excellent 36 yds. (32.9 m) and 60 yds. (54.9 m)

3M[™]**ATG Tape** 987

Application Techniques	• Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength.	
	• To obtain optimum adhesion, the bonding surfaces must be clean, dry, and well unified.	
	• Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.	
Storage	Store in original cartons at 70°F (21°C) and 50% R.H.	
Shelf Life	To obtain best performance, use this product within 18 months from date of manufacture.	
Recognition/ Certification	MSDS: 3M has not prepared a MSDS for this product which is not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, the product should not present a health and safety hazard. However, use or processing of the product in a manner not in accordance with the directions for use may affect its performance and present potential health and safety hazards.	
	TSCA: This product is defined as an article under the Toxic Substances Control Act and therefore, it is exempt from inventory listing requirements.	
Product Use	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.	
Warranty and Limited Remedy	Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.	
Limitation of Liability	Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.	
0 1	This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.	
3M		

Industrial Business Industrial Adhesives and Tapes Division

3M Center, Building 21-1W-10, 900 Bush Avenue St. Paul, MN 55144-1000 800-362-3550 • 877-369-2923 (fax) www.3M.com/industrial



Recycled Paper 40% pre-consumer 10% post-consumer





Общество с ограниченной ответственностью «МосЧип» ИНН 7719860671 / КПП 771901001 Адрес: 105318, г.Москва, ул.Щербаковская д.З, офис 1107

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

http://moschip.ru/get-element

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж: moschip.ru moschip.ru_4

moschip.ru_6 moschip.ru_9