

SPECIFICATION CONTROL DRAWING

SCD

55A8040

Title WIRE, RADIATION-CROSSLINKED, MODIFIED ETFE-INSULATED,
NORMAL WEIGHT, GENERAL PURPOSE, 600 VOLT

Date 9-30-15

Revision J

This specification sheet forms a part of the latest issue of Raychem Specification 55A.




TABLE I. CONSTRUCTION DETAILS

PART NUMBER 1/	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	DIAMETER OF STRANDED CONDUCTOR (inch)	FINISHED WIRE		
				MAXIMUM RESISTANCE AT 20°C (ohms/1000 ft.)	DIAMETER (inch)	MAXIMUM WEIGHT (lbs/1000 ft.)
55A8040-8-*	8	41 x 24	.155 ± .005	1.09	.215 ± .014	29.0
55A8040-6-*	6	70 x 24	.206 ± .005	.641	.270 ± .015	44.0
55A8040-4-*	4	107 x 24	.255 ± .007	.427	.320 ± .016	65.8
55A8040-2-*	2	168 x 24	.320 ± .010	.268	.395 ± .018	97.0
55A8040-1-*	1	219 x 24	.358 ± .010	.214	.440 ± .018	125.
55A8040-0-*	0	259 x 24	.408 ± .012	.169	.490 ± .020	149.
55A8040-00-*	00	334 x 24	.466 ± .012	.133	.550 ± .022	189.
55A8040-000-*	000	427 x 24	.523 ± .012	.109	.615 ± .022	227.
55A8040-0000-*	0000	523 x 24	.575 ± .012	.085	.665 ± .022	269.

TABLE II. PERFORMANCE DETAILS

PART NUMBER 1/	BEND TESTING			
	MANDREL DIAMETER (inch) (± 3%)		WEIGHT (lb) (± 3%)	
	IMMERSION, LIFE CYCLE, AND ACCELERATED AGING	COLD BEND	IMMERSION, LIFE CYCLE, AND ACCELERATED AGING	COLD BEND
55A8040-8-*	3.00	6.00	3.00	6.00
55A8040-6-*	4.00	8.00	3.00	10.0
55A8040-4-*	5.00	10.0	3.00	10.0
55A8040-2-*	6.00	12.0	4.00	15.0
55A8040-1-*	7.00	13.0	4.00	15.0
55A8040-0-*	8.00	14.0	4.00	15.0
55A8040-00-*	9.00	16.0	4.00	15.0
55A8040-000-*	10.0	18.0	4.00	15.0
55A8040-0000-*	12.0	18.0	4.00	15.0

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C

Maximum continuous conductor temperature

VOLTAGE RATING: 600 volts (rms) at sea level

ACCELERATED AGING (CROSSLINKING PROOF): 300 ± 3°C for 7 hours

BLOCKING: 200 ± 3°C for 24 hours

BRAID COLOR: Light Yellow, munsell color limits 5Y 6/6 and 7.5Y 8/8

Dark Green, munsell color limits 5Y 3/2 and 5B 2/0.5

CONCENTRICITY: 70% (minimum)

FLAMMABILITY (Qualification Test): Procedure 1,

3 seconds (maximum); 3 inches (maximum); no flaming of facial tissue

HUMIDITY RESISTANCE: Insulation Resistance,

3000 megohms for 1000 ft. (minimum)

IMMERSION: Diameter increase 5% (maximum); no cracking, no dielectric breakdown

INSULATION ELONGATION AND TENSILE STRENGTH:

Total Insulation (primary insulation and jacket)

Elongation, 50% (minimum)

Tensile Strength, 5000 lbf/in² (minimum)

INSULATION FLAWS:

Primary Insulation,

Spark Test, 1.5 kV (rms)

Impulse Dielectric Test, 6.0 kV (peak)

Finished Wire,

Spark Test, 3.0 kV (rms)

Impulse Dielectric Test, 8.0 kV (peak)

INSULATION RESISTANCE (Qualification Test):

3000 megohms for 1000 ft. (minimum)

INSULATION THICKNESS: Total Insulation, 0.008 in. (minimum)

JACKET COLOR: White

LIFE CYCLE: 200 ± 3°C for 168 hours

LOW TEMPERATURE-COLD BEND (Qualification Test): -65 ± 3°C for 4 hours

SHRINKAGE: 200 ± 3°C for 6 hours, 0.125 in. (maximum) in 12 inches

SMOKE TEST: 200 ± 2°C, no visible smoke

SURFACE RESISTANCE: 500 megohms-in. (minimum), both readings

THERMAL SHOCK RESISTANCE (Qualification Test): 150 ± 3°C,

0.100 in. (maximum), AWG 8

0.125 in. (maximum), AWG 6-0000

VOLTAGE WITHSTAND (Post Environmental): 2500 volts (rms), 60 Hz

1/ PART NUMBER:

The "*" in the part numbers in Tables I and II shall be replaced by a color code designator.

5D shall be used to designate dark green.

Example: AWG 00, dark green: 55A8040-00-5D

AWG 00, white: 55A8040-00-9

Данный компонент на территории Российской Федерации

Вы можете приобрести в компании MosChip.

Для оперативного оформления запроса Вам необходимо перейти по данной ссылке:

<http://moschip.ru/get-element>

Вы можете разместить у нас заказ для любого Вашего проекта, будь то серийное производство или разработка единичного прибора.

В нашем ассортименте представлены ведущие мировые производители активных и пассивных электронных компонентов.

Нашей специализацией является поставка электронной компонентной базы двойного назначения, продукции таких производителей как XILINX, Intel (ex.ALTERA), Vicor, Microchip, Texas Instruments, Analog Devices, Mini-Circuits, Amphenol, Glenair.

Сотрудничество с глобальными дистрибьюторами электронных компонентов, предоставляет возможность заказывать и получать с международных складов практически любой перечень компонентов в оптимальные для Вас сроки.

На всех этапах разработки и производства наши партнеры могут получить квалифицированную поддержку опытных инженеров.

Система менеджмента качества компании отвечает требованиям в соответствии с ГОСТ Р ИСО 9001, ГОСТ РВ 0015-002 и ЭС РД 009

Офис по работе с юридическими лицами:

105318, г.Москва, ул.Щербаковская д.3, офис 1107, 1118, ДЦ «Щербаковский»

Телефон: +7 495 668-12-70 (многоканальный)

Факс: +7 495 668-12-70 (доб.304)

E-mail: info@moschip.ru

Skype отдела продаж:

moschip.ru

moschip.ru_4

moschip.ru_6

moschip.ru_9